

MOTIVI GLOSS LAMINATE POSTFORMING LAMINATES less than 2 mm thick, according to EN 438-3:2008, consisting of the surface layer on one side, having decorative colours are impregnated with melamine based resins and core made of layers of kraft paper impregnated with phenolic based resins. The back of the sheets is made suitable for adhesive bonding to substrates. They are available the postforming types HGP and VGP

HGP	Horizontal Grade Postforming Laminate	EXAMPLES OF TYPICAL APPLICATIONS Kitchen and office working surfaces, restaurant and hotel tables, doors and wall coverings in public areas, interior walls of public transport vehicles
VGP	Vertical Grade Postforming Laminate	EXAMPLES OF TYPICAL APPLICATIONS Front panels for kitchen, office and bathroom furniture, wall coverings, ceiling panels, shelves and furniture elements

PROPERTIES	TEST METHOD	PROPERTY OR ATTRIBUTE	UNIT (max or min)	VALUES	
				HGP	VGP

SURFACE QUALITY

Surface Quality	EN 438-3	Spots, dirt and similar surface defects	mm ² /m ²	≤1	
		Fibres, hairs and scratches	mm/m ²	≤10	

DIMENSIONAL TOLERANCES

Dimensional Tolerances	EN 438-2.5	Thickness tolerance	mm	0,5 ≤ t ≤ 1: ±0,10	
			mm	1,0 < t < 2,0: ±0,15	
	EN 438-2.6	Length and width	mm	+10/-0	
	EN 438-2.7	Straightness of edges	mm/m	≤1,5	
	EN 438-2.8	Squareness	mm/m	≤1,5	
EN 438-2.9	Flatness	mm/m	≤60		

GENERAL PROPERTIES

Resistance to surface wear	EN 438-2.10	Initial Point	Revolutions	≥150	≥50
		Wear Value	Revolutions	≥350	≥150
Resistance to immersion in boiling water	EN 438-2.12	Appearance-Gloss Finish	Rating (min)	3	
		Appearance-Other Finish	Rating (min)	4	
Resistance to water vapour	EN 438-2.14	Appearance-Gloss Finish	Rating (min)	3	
		Appearance-Other Finish	Rating (min)	4	
Resistance to dry heat (180°C)	EN 438-2.16	Appearance-Gloss Finish	Rating (min)	3	
		Appearance-Other Finish	Rating (min)	4	
Resistance to wet heat (100°C)	EN 12721:2010	Appearance-Gloss Finish	Rating (min)	3	
		Appearance-Other Finish	Rating (min)	4	
Dimensional stability at elevated temperature	EN 438-2.17	Cumulative dimensional change	Longitudinal %	≤0,55	≤0,75
		Cumulative dimensional change	Transversal %	≤1,05	≤1,25
Resistance to impact with small diameter ball	EN 438-2.20	Spring Force	N (min)	≥ 20	≥ 15
Resistance to impact with large diameter ball	EN 438-2.21	Drop height	mm	≥800	≥600
		Indentation diameter	mm	≤10	≤10
Resistance to cracking under stress	EN 438-2.23	Appearance	Rating (min)	4	
Resistance to scratching	EN 438-2.25	Appearance	Rating (min)	3	2
Resistance to staining	EN 438-2.26	Appearance-Group 1&2	Rating (min)	5	
		Appearance-Group 3	Rating (min)	4	
Light fastness (Xenon-arc)	EN 438-2.27	Contrast	Grey scale rating	4	
Resistance to cigarette burns	EN 438-2.30	Appearance	Rating (min)	3	
Formability	EN 438-2.31-32	Radius	L(parallel to fibre direction) mm	≤10 x nominal thickness	
		Radius	T (right angles to fibre direction) mm	≤20 x nominal thickness	
Resistance to blistering	EN 438-2.33-34	Time to blister	Seconds-nominal thickness < 0,8mm	≥10	
		Time to blister	Seconds-nominal thickness ≥ 0,8mm	≥15	
Density	EN ISO 1183	Density	g/cm ³	≥1,35	